



SPL Bohumín

1.máje 432, CZ-735 31 Bohumín, Czech Republic
Phone +420 596 014 627, e-mail info@spl-bohumin.cz, www.spl-bohumin.cz

CERTIFICATE No 04 – 14

REFERENCE MATERIAL OF FREE-CUTTING STEEL for solid sample spectrometry, combustion and wet-way methods

SPL CM-15C

Certified fully compliant with the ISO Guide 35 definition of Reference Material – with the values confirmed and their uncertainties assessed.

Compliant with the ISO Guide 35 definition of Reference Material.

Intended for calibration and the control of matrix-match and of the state of statistic regulation in the automated spectrometry of low alloy steel from a plane of solid sample. They may not substitute CRM in establishing traceability of the results. A single analysis area of at least 4 mm in diameter defines the minimum sample intake. May be used for combustion and wet-way methods too.

Manufactured from the commercially available rolled steel bars.

Supplied as discs of 37 mm in diameter and in 10 or 25 mm standard heights. With size on option of height up to 50 mm on request, steel chips for combustion and wet-way methods.

Homogeneity (random and trend, within- and between- samples) was tested by various analytical techniques of adequate repeatability. Its uncertainty contribution, when statistically significant, was combined to the ultimate uncertainty statement. The RM are **stable** by a nature of material.

Characterised by an interlaboratory experiment of the expert laboratories listed below by various spectrometric (AES spark, glow discharge, XRF) and alternative (combustion, thermoevolution, wet-way) standard methods, with values **traceable** to values of the adequate CRM (CZ 2001, 2003 - 2008, BAS, Brammer Standard).

ENVIFORM a.s., Třinec, Czechia

HUKOS s.r.o., Ostrava, Czechia

LITHEA s.r.o., Brno, Czechia

VÍTKOVICE TESTING CENTER s.r.o., Ostrava, Czechia

ZPS-SLÉVÁRNA, a.s., Zlín, Czechia

ŽĎAS a.s., Žďár nad Sázavou, Czechia

Certified values in % m/m, tabulated over page in bold, are robust means of a minimum five laboratory means accepted by a technical scrutiny, each of them based on at least five independent results. They are rounded to the same digit as their respective:

Uncertainty (tabulated in regular below the respective value), expressed as a \pm half width interval of combined uncertainty, expanded by a coverage factor $k = 2$ (corresponding to 95% probability level). It does not exceed 1,5 multiple of the typical uncertainty of the matching CRM.

Non-certified values in regular without the uncertainty statement do not meet the requirements for certification and are intended for the matrix information.

RM	C	Mn	Si	P	S	Cu	Cr	Ni
CM-15C	0,075 0,006	1,13 0,04	0,006 0,002	0,063 0,003	0,32 0,01	0,141 0,004	0,052 0,003	0,072 0,004
RM	Al	Mo	W	V	Ti	Co	As	Sn
CM-15C		0,021 0,003				0,01		
RM	B	Nb	Pb	Sb	Zr	Ca	Ta	N
CM-15C			0,29 0,01					

User instruction: the working surface of the RM must be prepared before the analysis in the same way as the analysed sample in accordance with the particular analyser manual. Storage in dry and non-corrosive environment is recommended.

Produced by: SPL, the authorised producer of CRM for the Czech Metrology Institute and the provider of the interlaboratory Proficiency Testing accredited by the Czech Accreditation Institute, in a strict compliance with ISO/IEC 17025, 17043 and in particular with ISO Guide 34.

Responsible person: Martin Bogumský

Issued in Bohumín on September 2014

Ing. Iva Bogumská - SPL

Služby pro laboratoře

1. máje 432

739 31, Bohumín, CZ

IČO: 46605134 DIČ: CZ515414033