



SPL Bohumín

1.máje 432, CZ-735 31 Bohumín, Czech Republic
Phone +420 596 014 627, e-mail info@spl-bohumin.cz, www.spl-bohumin.cz

CERTIFICATE No 02 – 16

REFERENCE MATERIAL OF MANGANESE STEEL for solid sample spectrometry, combustion and wet-way methods

SPL SP-2C

Certified fully compliant with the ISO Guide 35 definition of Reference Material – with the characterization for determining the property values and their associated uncertainties.

Intended for calibration, matrix-match verification and statistical process control of low alloy steel spectrometric analysis from a plane of solid sample. They may not substitute CRM in a statement of metrological traceability, method validation. A single analysis area of at least 4 mm in diameter defines the minimum sample intake. They may be used for combustion and wet-way methods too.

Manufactured by casting to a special ingot with discarding of the parts, which have been suspected inhomogenous and the rest has been machined to the samples of the ultimate size.

Supplied as discs 37 mm in diameter and 10 or 25 mm of standard height, as option is possible up to 50 mm high and on request steel chips for combustion and wet-way methods.

Homogeneity (random and trend, within- and between- samples) was tested by various analytical techniques of adequate repeatability. Its uncertainty contribution, when statistically significant, was combined to the ultimate uncertainty statement. The RM are stable by a nature of material.

Characterised by inter-laboratory study of the expert laboratories listed below by various spectrometric methods (AES spark, glow discharge, XRF) and alternative methods (combustion, thermoevolution, wet-way) standard methods, with measurements metrological **traceable** to adequate CRM (CZ 2001, 2003 - 2008, BAS, Brammer Standard).

ARCELORMITTAL, Ostrava, Czech Republic

ENVIFORM, Třinec, Czech Republic

HAMAG, Zlín, Czech Republic

HUKOS, Ostrava, Czech Republic

INSTITUT METALURGII ŻELAZA, Gliwice, Poland

INSTITUTE FOR CRM, Yekaterinburg, Russia

LITHEA, Brno, Czech Republic

US STEEL KOŠICE-LABORTEST, Košice, Slovakia

ZPS-SLÉVÁRNA, Zlín, Czech Republic

Certified values in % m/m, tabulated below in bold, are robust means of a minimum five accepted laboratory means. They are rounded to the same digit as their uncertainty statement.

Uncertainty is expressed as a $\pm$ half width interval combined from the standard uncertainty, expanded by the coverage factor $k = 2$ (corresponding to 95% level of confidence). It does not exceed 1,5 multiple of the typical uncertainty of the matching CRM.

Non-certified values in regular without the uncertainty statement do not meet the requirements for certification and are intended for the matrix information.

RM	C	Mn	Si	P	S	Cu	Cr	Ni	Al
SP-2C	1,40 0,03	14,50 0,21	0,29 0,02	0,037 0,003	0,016 0,002	0,35 0,03	1,56 0,03	0,050 0,003	0,030 0,002
RM	Mo	W	V	Ti	Co	As	Sn	B	Nb
SP-2C	0,050 0,002	0,033 0,005	0,051 0,003	0,014 0,001	0,044 0,003	<i>0,005</i>	0,037 0,003	<i>0,003</i>	
RM	Pb	Sb	Zr	Bi	Zn	N	Ca		
SP-2C						0,027 0,001			

User instruction: the surface of the specimens and RM should be prepared in a similar manner in accordance with manufacture's instructions of spectrometers. It is recommended to storage of RM in dry and non-corrosive conditions.

Produced by: SPL, the authorised producer of CRM for the Czech Metrology Institute and the provider of the interlaboratory Proficiency Testing accredited by the Czech Accreditation Institute, in a strict compliance with ISO/IEC 17025, 17043 and in particular with ISO Guide 34 and 35.

Responsible person: Martin Bogumský

Issued in Bohumín on March 2016

Ing. Iva Bogumská - SPL

Služby pro laboratoře

1. máje 432

735 31 Bohumín, CZ

IČO: 46605134 DIČ: CZ515414033